




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷: D04H 1/54, 13/00, 3/04, 1/74	A1	(11) International Publication Number: WO 00/63478 (43) International Publication Date: 26 October 2000 (26.10.00)
(21) International Application Number: PCT/US00/10378 (22) International Filing Date: 18 April 2000 (18.04.00) (30) Priority Data: 60/129,941 19 April 1999 (19.04.99) US 09/551,075 18 April 2000 (18.04.00) US (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: TRAVIS, Anthony; 2 Newlands Road, Cockermouth, Cumbria CA13 0AH (GB). MCNICHOLL, Desmond, Bernard; "Braehead", Papcastle, Cockermouth, Cumbria CA13 ONU (GB). (74) Agent: STRICKLAND, Frederick, D.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: CA, ID, JP, KR, VN, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>

(54) Title: A STRETCH RECOVERABLE NONWOVEN FABRIC AND A PROCESS FOR MAKING

**(57) Abstract**

A process for imparting a desired degree of stretchability and stretch recovery to a nonwoven material by shrinking the nonwoven material by heating the material in a wet treating step and then permitting the material to dry in a relaxed state and a nonwoven material exhibiting such stretchability and stretch recovery properties.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Larvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

A STRETCH RECOVERABLE NONWOVEN FABRIC**AND A PROCESS FOR MAKING****FIELD OF THE INVENTION**

5

This invention relates to nonwoven fabrics having little or no stretchability that can be rendered stretch recoverable.

10

BACKGROUND OF THE INVENTION

It is well known that nonwoven fabrics have significant cost advantages over woven and knit fabrics, however nonwovens do not typically have good elastic properties. However, there are applications where the combination of low cost of nonwovens yet with some amount of elasticity is desirable.

US patent 5,491,016 describes a heat shrinkable nonwoven which comprises outer layers of thermoplastic staple fibers and an inner layer containing heat shrinkable fibers. In general, this patent discloses heating a point-bonded nonwoven web containing heat-shrinkable fibers to cause shrinkage between the bond points. The layers are point-bonded together at spaced locations and then uniformly heated in a relaxed state resulting in increased bulk. The fibers in the layers are carded or oriented substantially in the machine direction of the web. The preferred heat shrinkable fiber is either a 2-component side-by-side or sheath/core fiber. The amount of bicomponent fibers disposed in the central layer is less than 25% of the basis weight of the entire web. The pattern of the point-bonding is considered important - the pattern

should extend across the web in a cross machine direction or at an acute angle thereto, such as in a zigzag or chevron pattern. This results in point-bonding of fibers relative to the machine direction, with maximum bulking or decrease in length in the machine direction, with little or no decrease in width in the cross-machine direction. The heating in a relaxed state is conducted at a temperature sufficient to cause maximum shrinkage of the bicomponent fibers, without having any significant thermal effect on the staple fibers. For example, a stream of hot air may be passed through the web, or the web may be gradually heated on rollers. Other acceptable methods include radiant heating under conditions that prevent excessive heating of the outer layers. The shrinkage of the bicomponent fibers results in shrinkage between the bond sites. In a specific example, during the heating step, the feed of the web into the heater and the recovery rate from the heater to a cooling zone was regulated to accommodate about 20% shrinkage of the web in the machine direction.

This reference addresses relaxation of shrinkage to increase bulk but it is not relevant to making a substantially non-stretchable material both stretchable and stretch-recoverable.

BRIEF DESCRIPTION OF THE DRAWINGS

The invention may be more easily understood by reference to the accompanying drawing, which is a schematic of an apparatus for performing certain aspects of the invention.

SUMMARY OF RESULTS

In one aspect of this invention, there is provided a stretch-recoverable nonwoven fabric comprising staple fibers, wherein the fabric is thermally point-bonded with a geometric pattern and has a stretchability of about at least 3% in the cross-machine direction and substantially 100% stretch-recoverability.

In another aspect of this invention, there is provided a stretch recoverable composite fabric comprising a nonwoven fabric comprising staple fibers, wherein the fabric is thermally point-bonded with a geometric pattern and an elastic woven fabric, wherein the nonwoven fabric and the woven fabric are laminated together, thereby forming the composite fabric.

In yet other aspect of this invention, there are provided processes for making the aforementioned fabrics.

DETAILED DESCRIPTION OF THE INVENTION

It is an object of this invention to process a nonwoven fabric so as to achieve a certain amount of stretchability and stretch recovery. It is a particular object that the stretch recoverable nonwoven fabric be useful for shoe liners. Some terms should be defined at this point. "Stretchability" is the degree of stretch that the fabric can undergo without permanent deformation. In this invention, this is essentially the same as the degree of "shrinkage" that the fabric experiences during the treatment that will be described below. "Stretch recovery" is a measure of the extent to which the fabric recovers to its original length after stretching, in other words - its elasticity.

In order to impart a degree of stretchability into nonwoven fabrics, the process will entail a treatment

wherein the nonwoven fabric is shrunk. Typically, such a nonwoven fabric would remain in the shrunken condition. However, it has been found that the disclosed process can render a shrunken nonwoven fabric stretch recoverable in later use by allowing the fabric to shrink in a controlled manner.

A fabric that can be used is a nonwoven made from polyamide staple fiber. Examples of suitable polyamide fibers include nylon 6 staple fibers, nylon 66 staple fibers, nylon 6/nylon 66 sheath/core staple fibers, and blends thereof. The bicomponent fibers would be preferred and would preferably comprise at least 30% of the fabric. Preferably, the staple fiber length is between about 50 and 100 mm with the fiber size between about 1 and 10 decitex (dtex). The starting material for this invention is formed from staple fibers that are processed into a web and thermally point-bonded.

This is generally depicted in the figure, which includes elements that are well known to those of ordinary skill in the nonwovens art, and particularly for carded nonwovens. The staple fibers are run through carding machine 12 to form carded web 11. Although the figure shows two carded webs 11 and 13 being fed into crosslapper 14, it is understood that carded web 13 is also the product of a carding machine. The web 11 along with carded web 13 is passed into the crosslapper 14 and a multilayered web 17 is formed. The double-edged arrow shows that the crosslapper moves back and forth across the width of belt 20, which travels in a direction 90 to the crosslapper movement. The web 17 is typically, passed through a needle-puncher 18. Needle punching, although desirable, is not required and other consolidation methods can be used. Needle-punched web 19 is then fed into nip 24

formed by rolls 22 and 26 is thermally point-bonded into web 23 and then wound up on roll 26. The fabric is point-bonded by passing the fabric between a backing roll and a bonding roll having the desired pattern embossed thereon. The point-bonding provides a particular pattern, which facilitates shrinkage of the point-bonded nonwoven fabric during wet processing. The bonding temperature is set according to the fiber being used; for example, nylon 6 and nylon 66 melt at 220 C and 260 C, respectively. Instead of the nylon fibers, 100% polyester or 100% polypropylene could be used or blends with the various forms of nylon fibers as noted above can also be used. In certain cases acrylic, cotton or wool can be used.

15

The bonding pattern is selected to allow the fibers to bulk up between the bond points resulting in a decrease in the dimension of the fabric in substantially one direction. Certain patterns work and others do not. For example, it has been found that certain regular geometric patterns such as pique work whereas certain patterns having a random pattern do not work. The pique pattern, which is the preferred pattern, is registered under United States Trademark 1,413,427. The pique pattern provides point-bonds that are approximately 2.54 mm long and 0.38 mm wide, with 15 bonds per cm² for a total bonded area of approximately 15 percent of the total surface. The point-bonds can be larger however; the total point-bonded area is preferably less than about 25% and preferably between about 13 and 17%. As the point-bonded area increases there is a corresponding decrease in the ability of the fabric to shrink. Other patterns that can be used are designated barkweave and

fineweave. The barkweave pattern provides point-bonds that are approximately 1.91 mm long and 0.76 mm wide, with a total bonded area of approximately 7-9% percent of the total surface. The fineweave pattern provides
5 point-bonds that are approximately 1.09 mm long and 0.43 mm wide with a total bonded area of approximately 4-1/2 to 6-1/2 percent of the total surface. With reference to the figure it is noted that for making the pique pattern top roll 22 is embossed and opposing
10 bottom roll 26 is plain. On the other hand, for making the barkweave and the fineweave patterns, both roll 22 and 26 are embossed. It is also possible to perform this process with continuous filament fibers that are thermally point-bonded.

15 A point-bonded staple nonwoven web is allowed to shrink by about 3-10%, preferably 5-10%, and more preferably 5-6% in one direction (typically, the width, i.e., the cross machine direction) by heating the fabric in a wet treatment step. The wet treatment can
20 be any wet process that causes the fibers to bulk up between the bond points, resulting in shrinkage of the point-bonded fabric. However, a convenient method to accomplish the shrinkage is during the dyeing process because it is often desirable to color the fabrics. Any
25 fibers that cause the fabric to shrink when heated in a wet process can be used.

After the wet-treatment, the fabric is run through a drying step. While it would in most cases be more efficient to dry the fabric at an elevated temperature,
30 the primary point is to allow the fabric to dry in a relaxed state. The fabric should be dried in a relaxed state and not stretched back to its original size, i.e., the fabric would maintain its shrunken dimension once dry. It is acceptable for the fabric to be re-

stretched slightly during drying so long as the final fabric has a stretchability of at least about 3%, and preferably at least about 5%. The resulting nonwoven fabric is stretchable to the approximate extent and in the direction that it was shrunk. As noted above, the width is the dimension that is usually shrunk.

However, there may be some minor degree of stretching (on the order of about 1%) in the machine direction as a result of pulling the fabric through the drying step.

However, it should be noted that the nonwoven fabric can be similarly rendered stretchable in the length (i.e., machine direction). Further, the nonwoven fabric can be rendered stretchable in both the machine and cross-machine directions.

In another embodiment, the stretchable nonwoven fabric as provided above can be laminated to a stretch-recoverable fabric made using an elastic material, such as a spandex/cotton blend that can be woven, knit, etc., to provide a stretch-recoverable laminate.

LYCRA® spandex is an example of what can be used. LYCRA® is a registered trademark of E.I. du Pont de Nemours and Company of Wilmington, DE. Any elastic fiber that imparts some degree of stretch to the laminate is desirable. The nonwoven fabric and the elastic material can be joined to form the laminate with adhesives, ultrasonic bonding, by needling, or any other method that does not interfere with the stretch-recovery imparted to the material. There are several stretchable adhesives available that will work for this purpose. Hot melt adhesives are also suitable and can be applied intermittently without substantially reducing the stretch recovery of the fabric. Examples of adhesives that can be used are polyolefins and copolyamides.

Yet another embodiment is to blend spandex (or other elastic staple fibers) with nylon (or other polymer) staple fibers. The elastic fiber would be present at about 5% of the total weight of the nonwoven fabric. The nonwoven point-bonded fabric would be formed from the mixture of the fibers and then treated as described above. The point bonding locks the spandex fibers into the fabric and the stretchability and stretch recovery are provided between the bod point of the spandex. The presence of the LYCRA® spandex allows the final fabric to recover more fully and more repeatably after being stretched in use. While it is preferable to achieve 100% stretch recovery a slightly lower percentage of stretch recovery may be considered acceptable.

The stretch-recoverable fabric can be made with an elastic material laminated to it or with blended-in elastic fibers. In which case the resultant fabric has increased stretchability as well as repeatable stretch recovery properties. Regardless, the stretch-recoverable fabric allows use in more molded shoe designs that would otherwise crease up at the tight contours in comparison to the conventional non-stretch-recoverable fabric.

Additionally, to provide the stretch recoverable fabric, elastomeric fibers can be incorporated into a different nonwoven web structure using several different methods. For one, a method is described by reference to apparatus 10 in the figure. A multiplicity of continuous elastomeric filaments is fed from a beam between nonwoven web 11 and 13 as the webs are fed into crosslapper 14. In this method the beam 30 is prepared and mounted in such a way as to be able to feed the fibers from the beam onto the

nonwoven webs as the web is fed into a crosslapper. The filaments 15 are first introduced into the webs while the crosslapper is stopped and then as the crosslapping operation proceeds the filaments are drawn between the webs. A multiplicity of elastic fibers is typically used. For example, when using spandex that comprises about 5 weight percent of the web about 300 filaments of 22 decitex each can be used. Such an arrangement would be applicable to a full-scale operation where the nonwoven web has a width of about 1-1/2 meters and a basis weight of about 150g/m². Accordingly, if the spandex were of a higher decitex, a lesser amount of filaments would be used. The beam 30 is driven at a speed to match the input speed of the nonwoven webs into the crosslapper. Suitable pre-tensioning devices control tension of the elastomeric fibers.

In another method, layers of a nonwoven web can be used to unwind continuous filament elastomeric fibers directly from bobbins (not shown) as the nonwoven webs are fed into the crosslapper. In this method, bobbins (not shown) of the elastomeric fiber are positioned such that lengths of the fiber can be laid onto the same input lattice(s) of a crosslapper as the nonwoven web(s). Although not shown in the figure, a multiplicity of bobbins can be used wherein an individual filament is unwound from each bobbin. The axes of the bobbins would be at 90 degrees to the axis of beam 30, but the elastic fibers would be oriented in the same direction as when fed from the beam 30. The crosslapper operates by folding several layers of the nonwoven web into a multi-layered web 17. The motion of the crosslapper and the movement of the nonwoven web cause the elastomeric fibers to unwind from the bobbins ensuring that each layer of the nonwoven web contains

continuous filaments of elastomeric fiber. Suitable pre-tensioning devices control tension of the elastomeric fiber. When introducing the filaments from either the beam 30 or the bobbins, the filaments would be oriented in substantially the cross-machine direction relative to cross-lapped web 17.

Yet another method is feeding a scrim of elastomeric fibers onto a nonwoven web as the web is fed into a crosslapper. Although not depicted in The figure, this method incorporates a previously prepared scrim made of elastomeric fibers which has been wound onto a roll that would be positioned similarly to the beam 30. The scrim is unwound between the nonwoven webs as they are fed into the crosslapper. By using the scrim, it would be possible to achieve stretch recovery in both the cross-machine and machine directions. Tension of the scrim is achieved through a combination of unwinding speed and a pre-tensioning device.

In the aforementioned methods, after crosslapping the webs are needle-punched and then thermally bonded. Although preferred, it is not necessary to needle punch the crosslapped webs before they are point bonded. It should be further noted that

25

EXAMPLES

As noted above, stretchability is the degree of stretch that the fabric can undergo without permanent deformation. If the fabric experiences a reduction of 6% in width during wet treatment, then it can be stretched 6% in the width without permanent deformation; therefore it has a stretchability of 6%. Stretch recovery is a measure of the extent to which the fabric recovers to its original length after stretching, in other words - its elasticity. It

should be noted however that in this invention the "original" length is the reduced dimension achieved by the wet treatment. Stretch recovery was determined in the examples by the following method:

- 5 1. cut 10 samples 30 cm x 5 cm across the width of the fabric, the fabric having a width of 30 cm.
2. measure off and mark two lines 25 cm apart equidistant from each end of the sample, which is the gauge length.
- 10 3. insert the samples into jaws of an Instron test machine, aligning the upper and lower jaws with the lines marked on the sample.
4. stretch fabric as represented by the 25 cm gauge length to 26.5 cm at a speed of 20 cm/min.
- 15 5. release the fabric from the jaws after they have reached the 26.5 cm distance.
6. re-measure the gauge length marked on the fabric and determine the stretch recovery as follows.

20

$$\text{Stretch Recovery (\%)} = \frac{\text{Stretched Length} - \text{Length after recovery}}{\text{Stretched Length} - \text{Original Length}} \times 100$$

25

7. repeat for remaining 9 samples.
8. report the average of the ten samples.

Example 1

- 30 A needle-punched carded nonwoven fabric formed from nylon 66/6 core/sheath staple fibers (, 65 mm staple length, 3.3 dtex) and point-bonded with a pique pattern was used in this example. The fabric had a basis weight of 150 g/m². The point bonds were
- 35 approximately 2.54 mm long and 0.38 mm wide, with 15 bonds per cm² for a total bonded area of approximately 15 percent of the total surface.

- The point-bonded fabric was dyed in a winch dye bath. The winch was heated to 50 °C for 10 minutes,
- 40 the dye added, and the temperature maintained at 50 °C for an additional 10 minutes. The temperature was then

raised to a boil and the fabric was dyed at the boil for 60 minutes. During the dyeing process, the fabric was relaxed in both the length and width direction. The dyed fabric had shrunk by approximately 6% in the width
5 (cross-direction) from a starting fabric width of 147 cm to a dyed fabric width of 138 cm. Following dyeing, the fabric was wound under tension prior to drying.

The dyed fabric was unwound and dried at 170 °C using a pin stenter that was set at 138 cm width to
10 ensure that the fabric was dried in a relaxed state in the width direction. The residence time in the dryer was 30 seconds at 170 °C. The dried fabric had a width of 138 cm and a length essentially equal to the starting undyed fabric length. The dried fabric had a
15 stretchability of 6% in the width direction with a stretch recovery of 100%.

Example 2

20 The starting fabric for Example 2 was identical to that used in Example 1 except that the bi-component staple nonwoven was point-bonded in a barkweave pattern. The dyeing and drying procedure of Example 1 was followed to obtain a fabric that shrank 6% in width
25 at approximately constant length. The resulting fabric had a stretchability of 6% in the width direction, with 100% recovery.

Example 3

30 This example demonstrates preparation of a composite fabric formed by lamination of the stretchable point-bonded nonwoven of Example 1 and an elastic woven backing fabric using an adhesive web. The elastic backing fabric used contained 95 weight

percent cotton and 5 weight percent LYCRA® spandex (Mac Elasto Strong Purgata, supplied by Lenzi Egisto SPA, Italy).

The woven and nonwoven layers were laminated using a stretchable thermoplastic copolyamide adhesive web having a melting range of between 80 and 85 °C. The adhesive was applied at 25 ± 5 g/m². The laminate was formed under pressure at elevated temperature using a hot melt technique. The composite fabric had a stretchability of 10% in the width direction with a stretch recovery of 100%.

Example 4

This example demonstrates preparation of a composite fabric formed by lamination of the stretchable point-bonded nonwoven of Example 1 and an elastic woven backing fabric using an adhesive film. The elastic backing fabric used contained 95 weight percent cotton and 5 weight percent LYCRA® spandex (Mac Elasto Strong Purgata, supplied by Lenzi Egisto SPA, Italy).

The woven and nonwoven layers were laminated using a thermoplastic polyolefin continuous film having a melting range of between 85 and 90°C. The adhesive was applied at 25 ± 5 g/m². The laminate was formed under pressure at elevated temperature using a hot melt technique. The composite fabric had a stretchability of 10% in the width direction with a stretch recovery of 100%.

30


What is claimed is:

1. A stretch recoverable nonwoven fabric comprising staple fibers, wherein the fabric is thermally point-bonded with a geometric pattern and has a stretchability of about at least 3% in the cross-machine direction.
2. The fabric of Claim 1, wherein the stretchability is about at least 5%.
3. The fabric of Claim 1 or 2, wherein the stretch-recoverability is 100%.
4. The fabric of Claim 1, wherein the staple fibers are selected from the group consisting of nylon 6, nylon 66, nylon 6/nylon 66 sheath/core, polyester, polypropylene, and blends thereof.
5. The fabric of Claim 1, wherein the geometric pattern is selected from the group consisting of pique, barkweave and fineweave.
6. The fabric of Claim 1, further comprising elastic staple fiber present at about 5% of the total weight of the fabric.
7. The fabric of Claim 6, wherein the elastic staple fibers are spandex.
8. A stretch recoverable composite fabric comprising (a) a nonwoven fabric comprising staple fibers, wherein the fabric is thermally point-bonded with a geometric pattern and (b) an elastic woven fabric, wherein the nonwoven fabric and the woven fabric are laminated together, thereby forming the composite fabric.
9. The stretch recoverable composite fabric of Claim 8, wherein the woven fabric comprises about 95% cotton and about 5% spandex by weight of the woven fabric.
10. A process for imparting stretch-recoverability to a nonwoven fabric comprising the steps of providing the nonwoven fabric,

- thermally point-bonding the fabric in a geometric pattern,
heating the fabric in a wet treatment,
drying the fabric in a relaxed state.
- 5 11. The process of Claim 10, wherein the nonwoven fabric comprises staple fibers selected from the group consisting of nylon 6, nylon 66, nylon 6/nylon 66 sheath/core, polyester, polypropylene, and blends thereof.
- 10 12. The process of Claim 10, wherein the geometric pattern is selected from the group consisting of pique, barkweave and fineweave.
13. The process of Claim 10, wherein the heating step comprises dyeing.
- 15 14. The process of Claim 12, wherein the nonwoven fabric further comprises elastic staple fibers.
15. The process of Claim 13, wherein the elastic staple fibers are spandex.
16. A process for imparting stretch-recoverability to
20 a composite fabric comprising the steps of providing a nonwoven fabric,
thermally point-bonding the nonwoven fabric in a geometric pattern,
heating the nonwoven fabric in a wet treatment,
25 drying the nonwoven fabric in a relaxed state,
providing an elastic woven fabric,
laminating the elastic woven fabric to the nonwoven fabric, thereby forming the composite fabric.
- 30 17. The process of Claim 16, wherein the geometric pattern is selected from the group consisting of pique, barkweave and fineweave.
18. The process of Claim 16, wherein the laminating step is selected from the group consisting of
35 adhesive bonding, needling, and ultrasonic bonding.

1/1

FIG. 1



INTERNATIONAL SEARCH REPORT

Internat Application No

PCT/US 00/10378

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 D04H1/54 D04H13/00 D04H3/04 D04H1/74

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D04H B23B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 424 987 A (MATSUI YOSHINORI) 13 June 1995 (1995-06-13) column 5, line 51 - column 6, line 39 column 7, line 4 - line 52 column 12, line 17 - line 33 column 13, line 12 - line 68 figures 1-4; table 2	1,2,4,5
X	GB 1 208 785 A (MONSANTO COMPANY) 14 October 1970 (1970-10-14)	1,2
A	page 1, left-hand column, line 11 - page 2, right-hand column, line 80 claims 1,2,4,6,7; figures 1,2; example 1 -/-	3,6,7,10

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search

31 July 2000

Date of mailing of the international search report

09/08/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Joly, F

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/10378

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 851 935 A (SRINIVASAN RAMESH ET AL) 22 December 1998 (1998-12-22) column 2, line 28 -column 3, line 36 column 4, line 51 -column 7, line 22 figures 1-20	1,3
X	US 5 393 599 A (QUANTRILLE THOMAS E ET AL) 28 February 1995 (1995-02-28) column 3, line 21 - line 43 column 4, line 34 - line 53 column 6, line 1 - line 44 column 7, line 23 -column 10, line 18 column 11, line 1 -column 15, line 45 claim 1	1,2,4,8
X	WO 95 03443 A (FIBERWEB NORTH AMERICA INC ;QUANTRILLE THOMAS E (US)) 2 February 1995 (1995-02-02) page 5, line 19 - line 36 page 6, line 19 -page 7, line 19 page 9, line 8 -page 10, line 23 page 14, line 16 -page 15, line 17 page 23, line 32 -page 25, line 27 claims 1-3,24,28,29; figures 1-5	1-4,8
X	US 4 612 228 A (KATO HIROYASU ET AL) 16 September 1986 (1986-09-16)	10,11,13
A	column 7, line 23 -column 8, line 60 column 9, line 55 -column 10, line 15 column 11, line 45 - line 61 column 12, line 39 -column 15, line 60 figures 1-8R; example 4	16,18
X	US 4 634 612 A (NELSON DAVID L ET AL) 6 January 1987 (1987-01-06) column 2, line 65 -column 5, line 45 column 7, line 10 -column 8, line 18 figures 1,2	10,11,13
A	GB 2 085 938 A (ICI PLC) 6 May 1982 (1982-05-06) page 1, line 22 -page 3, line 37	1-5

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/10378

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5424987 A	13-06-1995	JP 2870320 B	17-03-1999
		JP 6111598 A	22-04-1994
		DE 69320743 D	08-10-1998
		DE 69320743 T	06-05-1999
		EP 0590608 A	06-04-1994
		KR 9616500 B	12-12-1996
GB 1208785 A	14-10-1970	BE 707249 A	01-04-1968
		DE 1635554 A	27-05-1971
		FR 1546119 A	
		LU 54976 A	05-08-1968
		NL 6716255 A	30-05-1968
US 5851935 A	22-12-1998	AU 4238497 A	19-03-1998
		EP 0921941 A	16-06-1999
		WO 9808678 A	05-03-1998
		US 6025050 A	15-02-2000
US 5393599 A	28-02-1995	US 5334446 A	02-08-1994
		AU 7335994 A	20-02-1995
		WO 9503171 A	02-02-1995
		AU 3482093 A	01-09-1993
		AU 3589193 A	01-09-1993
		BR 9305793 A	18-02-1997
		CA 2128731 A	05-08-1993
		CA 2128732 A	05-08-1993
		EP 0621910 A	02-11-1994
		EP 0621911 A	02-11-1994
		JP 7503291 T	06-04-1995
		JP 7503292 T	06-04-1995
		MX 9300386 A	01-08-1993
		WO 9315247 A	05-08-1993
		WO 9315248 A	05-08-1993
		WO 9503443 A	02-02-1995
		US 5431991 A	11-07-1995
WO 9503443 A	02-02-1995	US 5334446 A	02-08-1994
		AU 3482093 A	01-09-1993
		AU 3589193 A	01-09-1993
		BR 9305793 A	18-02-1997
		CA 2128731 A	05-08-1993
		CA 2128732 A	05-08-1993
		EP 0621910 A	02-11-1994
		EP 0621911 A	02-11-1994
		JP 7503291 T	06-04-1995
		JP 7503292 T	06-04-1995
		MX 9300386 A	01-08-1993
		WO 9315247 A	05-08-1993
		WO 9315248 A	05-08-1993
		US 5393599 A	28-02-1995
		US 5431991 A	11-07-1995
US 4612228 A	16-09-1986	JP 1472004 C	27-12-1988
		JP 58169557 A	06-10-1983
		JP 63019621 B	23-04-1988
		AT 49783 T	15-02-1990
		CA 1207996 A	22-07-1986
		DE 3381143 D	01-03-1990

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/10378

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4612228 A		EP 0090397 A US 4476186 A	05-10-1983 09-10-1984
US 4634612 A	06-01-1987	AU 590259 B AU 5543486 A BR 8606620 A CA 1248438 A DE 3685292 A EP 0219508 A JP 8014070 B JP 62502481 T WO 8606115 A	02-11-1989 05-11-1986 11-08-1987 10-01-1989 17-06-1992 29-04-1987 14-02-1996 24-09-1987 23-10-1986
GB 2085938 A	06-05-1982	NONE	